



PROPERTIES

Natural white cement-bound modelling paste for artistic design

APPLICATIONS

Smoothing of the surface and garnishing of details on concrete sculptures

Applicable for indoor and outdoor use.

COMPOSITION

Binder according to DIN EN 197, quartzitic aggregates according to DIN EN 12620, admixtures

SUBSTRATE / FORMWORK

When concreting onto existing concrete, the substrate must be clean, load-bearing and dust-free.

For a good bond with the substrate, it is recommended to precoat the substrate with a slurry consisting of PÜPPI and water and apply the fresh mortar on top, wet in wet. The slurry should have approximately the consistency of wall paint.

If the substrate does not have sufficient roughness, a cement slurry may be insufficient as a contact bridge. In this case, the substrate should be mechanically roughened beforehand or provided with a rough surface by applying a thin layer of KLEMO adhesive mortar.

VERARBEITUNG

Working temperature

Do not apply at air, material and substrate temperatures below +5 °C and above +30 °C.

Working time

approx. 60 minutes (times refer to +20°C and 65% relative humidity.) Mortar that has already set may be slightly moistened again within this time, kneaded and further processed.

Mixing / Preparation

Mix dry mass with max. 250 ml clean water per kg to a soft paste-like consistency. It is recommended to mix only small quantities at a time in a plaster cup with a metal spatula. To achieve a firmer consistency if required, dry mass can be kneaded in by hand afterwards.

Up to 40 g of cement-compatible colour pigments can be added per kg of dry mass.

Application / Processing

The material is applied quickly immediately after mixing. In case of multi-layer application, keep a time interval of about one day between the layers and pre-wet the substrate with slurry.

Setting / Hardening

Protect from too rapid water extraction by sun, wind or draught.

Low temperatures delay, high temperatures accelerate solidification and hardening.

Tool cleaning

Clean tools and equipment with water immediately after use.

Other information

No additives may be added.

However, the addition of up to 15 % RAPIZEM accelerator is permissible if required.

CONSUMPTION / YIELD

Consumption: approx. 1.7 kg/l

Yield: 2.7 l wet mortar per 4.5 kg bag

TECHNICAL DATA

Processing temperature:	+5 °C to +30 °C
Working time at 23 °C:	approx. 60 minutes
Water requirement:	approx. 1.125 litres per 4.5 kg
Mixing time:	approx. 1 minute
Compressive strength after 28 days:	≥ 6.0 N/mm ²
Grain size:	flour fine
Hue:	natural white

DELIVERY FORM

4.5 kg bag

STORAGE

Store in a dry and appropriate place.

Can be stored for at least 12 months from the date of production in the sealed original container.

SAFETY INSTRUCTIONS

The product reacts strongly alkaline with moisture/water. Therefore protect eyes and skin. Wear rubber gloves when applying the product manually. In case of contact with skin, rinse with plenty of water. In case of eye contact, consult a doctor immediately. Observe further instructions in the safety data sheet.

GISCODE: ZP1 (cementitious products, low in chromate).

DISPOSAL

Dispose of in accordance with official regulations. Empty containers should be recycled. Material residues can be disposed of according to the Waste Catalogue Ordinance under waste code 17 01 01 (concrete) or 10 13 14 (concrete waste and concrete slurry).

GENERAL INSTRUCTIONS

The information in this leaflet only represents general recommendations. Should any questions arise in a specific application, please contact our responsible technical sales consultant or our online forum <https://betonsprechstunde.moertelshop.com>. Due to the use of natural raw materials, the stated values and properties may be subject to fluctuations. All information is based on our current knowledge and experience and refers to professional application and normal use. All information is non-binding and does not release the user from the obligation to check the suitability of the product for the intended use. A guarantee for the general validity of all information is excluded with regard to different weather, processing and object conditions. We reserve the right to make changes within the scope of further product and application technology developments. The general rules of construction technology, the applicable standards and guidelines as well as technical processing guidelines must be observed. With the publication of this technical data sheet, previous editions lose their validity. For the latest information, please refer to our website www.moertelshop.com.

Effective date: 6/12/2021, Version: 1.0 (replaces all previous versions)